

Topilene® J640A**Polypropylene Block Copolymer**
For Injection Molding Applications**Product Description**

Topilene® J640A is a specially designed polypropylene block copolymer that features high flowability and balanced mechanical properties. It is suitable for injection molding applications. **Topilene® J640A** complies with FDA requirements in the code of Federal Regulations in 21 CFR 177.1520 for food contact.

Characteristics

Typical Application Automotive parts(Pillars, Battery case, etc), Industrial articles(Container, Crate, Pallet, etc), Electric appliances(Cleaner, Refrigerator, Washing machine, etc), Stationery, Housewares, Food containers, General goods

Features Good flowability / Excellent stiffness / High impact strength / UL 94HB

Typical Properties

Resin Properties	Method	Value	Unit
Melt Index(230°C, 2.16kg)	ASTM D1238	18.0	g/10min
Density	ASTM D792	0.90	g/cm ³
Tensile Strength at Yield	ASTM D638	270	kg/cm ²
Flexural Modulus	ASTM D790	13,500	kg/cm ²
Notched Izod Impact Strength(23°C / -10°C)	ASTM D256	7.0 / 4.5	kg-cm/cm
Rockwell Hardness	ASTM D785	90	R-Scale
Heat Deflection Temperature	ASTM D648	105	°C

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG CHEMICAL CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG CHEMICAL CORPORATION. **Topilene®** is a registered trademark owned or used by HYOSUNG CHEMICAL CORPORATION.

Contacts

Head Office 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578

Tel: +82-2-2146-5451~7 Fax: +82-2-2146-5428

Online www.hyosungchemical.com

www.topilene.com

**HYOSUNG CHEMICAL**